

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 August 2001 (02.08.2001)

PCT

(10) International Publication Number
WO 01/55276 A1

(51) International Patent Classification⁷: C09J 153/02,
7/02, A61L 15/00

[US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US). COLEMAN, Kathryn, A. [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US).

(21) International Application Number: PCT/US01/02807

(22) International Filing Date: 29 January 2001 (29.01.2001)

(74) Agents: QUAN, Nancy, N. et al.; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/179,263 31 January 2000 (31.01.2000) US

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(71) Applicant (*for all designated States except US*): H.B. FULLER LICENSING & FINANCING, INC. [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): KROLL, Mark, S. [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US). ACEVEDO, Margarita [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US). CAMERON, Janelle, C. [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US). KAUFFMAN, Thomas, F. [US/US]; 142 Fairway, Harleysville, PA 19438 (US). LINDQUIST, Jeffrey, S. [US/US]; 8920 Zazibar Lane N., Maple Grove, MN 55311 (US). SIMMONS, Eugene, R. [US/US]; 1200 Willow Lake Boulevard, Box 64683, St. Paul, MN 55164-0683 (US). MALCOLM, David, B.

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: RADIATION CURABLE ADHESIVE COMPOSITIONS COMPRISING BLOCK COPOLYMERS HAVING VINYL FUNCTIONALIZED POLYDIENE BLOCKS

(57) Abstract: The invention is directed to a radiation curable adhesive composition comprising at least one vinyl modified block copolymer having a first polyvinyl aromatic block and a second polydiene block having vinyl functionality, and at least one tackifier. Optionally, the composition may comprise at least one second block copolymer that has not been vinyl modified, at least one plasticizer, and at least one wax. The invention is also directed to a double-faced label formed from the composition and the method of producing said label.

WO 01/55276 A1

Radiation Curable Adhesive Compositions Comprising Block Copolymers Having Vinyl Functionalized Polydiene Blocks

Field of the Invention

5 The present invention relates to a radiation curable adhesive composition comprising at least one vinyl modified block copolymer having polyvinyl aromatic (styrenic) endblocks and polydiene midblocks having vinyl functionality. The adhesive composition exhibits at least one of a variety of improved adhesive performance characteristics depending on the type and amount of the ingredients selected.

10

Background of the Invention

 "UV Crosslinkable Styrenic Block Copolymers . . . A Door to High Temperature Heat Resistant Hot Melt Adhesive Applications" by Martine Dupont, the Journal of the Adhesive and Sealent Council, Inc., 1997 Spring Convention, Pittsburgh, Pennsylvania, 15 March 23-26, 1997, pp 229-240, discloses compositions containing 25 to 35 wt-% of a block copolymer KX-222C, a solid hydrogenated tackifying resin Regalite R91 or MBG 264, a hydrogenated liquid resin Regalrez 1018, a photoinitiator Irgacure 651 and an antioxidant Irganox 1010. The composition exhibits the lowest viscosity of 10 Pa.s at 160°C.

20 U.S. Pat. No. 5,804,663 discloses radiation sensitive vinyl aromatic block copolymers and radiation curable adhesives, sealants, and coatings containing such block copolymers. The radiation sensitive block copolymers contain at least one block derived from vinyl aromatic monomer and at least one block derived from butadiene. The adhesive exhibits the lowest viscosity of 6.7 Pa.s at 160°C.

25

Summary of the Invention

 In one embodiment, the invention is directed to a radiation curable adhesive composition that is amenable to being applied at a low application temperature, i.e., an application temperature no greater than about 150° C. Preferably, the application 30 temperature is no greater than about 140° C and more preferably, no greater than about 130° C. The adhesive composition comprises from about 10 wt % to about 40 wt %, of at

least one vinyl modified block copolymer having polyvinyl aromatic (styrenic) endblocks and vinyl functionalized polydiene midblocks, and from about 20 wt% to about 90 wt% of at least one tackifier. The vinyl functionality of the polydiene block presents reactively favorable sites and is at a sufficient concentration such that the block copolymer

5 crosslinks substantially through the vinyl functionality upon exposure to radiant energy. The adhesive composition may further comprise at least one plasticizer. Preferably, from about 30 wt% to about 90 wt% of the ingredients comprised of the composition are liquids at ambient temperature. Preferably, the liquid ingredients comprise a mixture of at least one polydiene block compatible tackifier and at least one polyvinyl aromatic

10 block compatible plasticizer. The adhesive composition may further comprise up to about 40 wt %, preferably from about 5 wt % to about 40 wt %, more preferably from about 5 wt% to about 20 wt%, of at least one second polymer such that the total polymer content in the composition is at least about 15 wt %. The second polymer may also be radiation sensitive, i.e., able to substantially crosslink upon exposure to radiant energy, or may not

15 be radiation sensitive. The adhesive composition has a Brookfield viscosity of less than about 10,000 cps and preferably, less than about 6,000 cps at a temperature of about 160°C.

In another embodiment, the invention is directed to a radiation curable adhesive composition comprising from about 10 wt% to about 40 wt% at least one vinyl modified

20 block copolymer having at least two blocks, wherein the first block is a polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality, from about 10 wt% to about 80 wt% of at least one tackifier that is compatible with the polydiene block; and from about 10 wt% to about 40 wt% of at least one plasticizer. The plasticizer is preferably a polyvinyl aromatic block compatible plasticizer having

25 softening point of no greater than 100° C; a high molecular weight polydiene block compatible plasticizer having a weight average molecular weight of no less than about 20,000 g/mol, preferably, up to about 100,000 g/mol, such as polyisoprene, or mixtures thereof.

In yet another embodiment, the invention is directed to a radiation curable

30 adhesive composition comprising from about 10 wt% to about 40 wt% of at least one vinyl modified block copolymer having at least two blocks, wherein the first block is a

polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality; from about 5 wt% to about 40 wt% of at least one second polymer selected from the group consisting of styrenic block copolymers, ethylene/ α -olefin interpolymers, amorphous polyalphaolefins, interpolymers of ethylene, and mixtures thereof; and from
5 about 10 wt% to about 90 wt% of at least one tackifier.

In yet another embodiment, the invention is directed to a radiation curable adhesive composition comprising from about 10 wt% to about 50 wt% of at least one vinyl modified block copolymer having at least two blocks, wherein the first block is a polyvinyl aromatic block and the second block is a polydiene block having vinyl
10 functionality; from about 20 wt% to about 55 wt% of at least one tackifier; from about 10 wt% to about 40 wt% of at least one wax; and from about 0 wt% to about 35 wt% of at least one plasticizer. The adhesive is not substantially tacky at a temperature of lower than the cloud point of the wax. The adhesive exhibits high shear resistance at high temperature, therefore, is appropriate for stretchable labels.

15 In yet another embodiment, the invention is directed to a double-faced tape formed from a single radiation curable adhesive composition, said double-faced tape having a first surface and a second opposing surface, said first surface exhibiting a first 180° peel value and said second surface exhibiting a second 180° peel value that is greater than said first peel value, upon radiation curing; and to a method of producing the
20 double-faced tape comprising applying an adhesive composition onto a release-coated surface to form an adhesive film layer and curing the adhesive film such that the adhesive film exhibits different adhesive properties on one surface than the opposing surface.

In yet another embodiment, the invention is directed to a plastic wrap comprising a film and an adhesive composition disposed on one surface of said film, said adhesive
25 composition exhibits a storage modulus (G') of less than about 1×10^5 dynes/cm² at about 25°C. Preferably, the storage modulus is within the pressure sensitive adhesive region as defined by the Dahlquist criteria through a temperature range of from about 0°C to about 120°C.

In yet another embodiment, the invention is directed to a hook or loop substrate
30 bonded with a radiation curable adhesive composition of the invention.

In yet another embodiment, the invention is directed to a disposable article having at least one substrate bonded with a radiation cured adhesive composition of the invention, wherein said adhesive composition is in contact with an oil-based skin care ingredient.

5 The adhesive compositions of the invention are amenable to a variety of end-uses, particularly for pressure sensitive adhesives for high performance tapes and labels such as freezer-grade tapes and labels, and automotive adhesives as well as for various adhesive applications wherein adhesion to wet surface is desired, such as medical products that employ an adhesive.

10 The radiation curable adhesive compositions can be formulated to exhibit higher peel values, higher heat resistance, improved cold temperature properties particularly at temperatures below 0°C, improved adhesion to wet surfaces and/or improved solvent and plasticizer resistance.

15 **Description of the Drawings**

Figure 1 represents the storage modulus (G'), loss modulus (G'') and tan delta of the adhesive composition in Example 2 prior to curing.

20 Figures 2 and 3 represent the storage modulus (G'), loss modulus (G'') and tan delta of the adhesive compositions in Examples 6 and 20, respectively, prior to and after curing. The radiation induced crosslinking extends the storage modulus plateau. The rheogram of Example 2 after curing would demonstrate a similar effect.

25 Figure 4 depicts the curing exotherms of the adhesive composition in Example 6 at room temperature, 100°C and 160°C, respectively. The area under the curve represents the extent of the reaction. Only a fraction of the reaction take place at room temperature in comparison to elevated temperatures. However, no significant differences were found by increasing the temperature above 100°C.

Detailed Description of the Invention

30 The radiation curable adhesive composition of the invention comprises at least one vinyl modified block copolymer, at least one tackifier and optionally, at least one plasticizer.

The vinyl modified block copolymer comprises at least two blocks wherein the first block is a polyvinyl aromatic (styrenic) endblock and the second block is a polydiene mid-block that has been 1,2-vinyl modified, i.e., the resultant 1,2-vinyl double bonds dangle on polydiene mid-blocks. These dangling double bonds, or the vinyl functionality, present reactively favorable sites and are at a sufficient concentration such that the vinyl modified block copolymer crosslinks substantially through such vinyl functionality upon exposure to a radiant energy source. The polyvinyl aromatic block in the vinyl modified block copolymer is typically styrene. However, various alkyl-substituted styrenes, alkoxy-substituted styrenes, vinyl naphthalene, alkyl-substituted vinyl naphthalenes and the like are also suitable compounds for formation of the polyvinyl aromatic block. The polydiene block may be formed from a variety of conjugated diolefins containing from about 4 to about 24 carbon atoms, such as those disclosed by U.S. Patent No. 5,382,604, which is incorporated herein by reference. Typically, however, the conjugated diene is 1,3-butadiene and/or isoprene. The conjugated diene block is typically modified such that sufficient vinyl functionality is incorporated.

The structure of the vinyl modified block copolymer may be linear, multiblock, radial, multi-arm, or grafted in structure. Preferably, the vinyl modified block copolymer is a branched asymmetric molecule containing styrene-butadiene (SB) and homopolybutadiene arms having the general formula $(SB)_2B_2$ wherein the butadiene midblock has been 1,2-vinyl modified. Information concerning the synthesis, physical properties, compatibility with other ingredients, etc. is known from U.S. Patent No. 5,804,663, incorporated herein by reference. A preferred $(SB)_2B_2$ block copolymer is commercially available from Shell under the tradename Kraton® D-KX-222C. Although vinyl modified block copolymers having homopolybutadiene arms are preferred, other vinyl modified styrene-butadiene-styrene (SBS) block copolymers such as vinyl modified random styrene-butadiene multiblock (S-B-S-B-S) block copolymers may also be employed provided that the polydiene midblock contains a sufficient concentration of the vinyl functionality that crosslink upon exposure to radiant energy. Alternative vinyl modified block copolymers that may be employed alone or in combination with Kraton® D-KX222C include, such as a vinyl modified random styrene-butadiene multiblock (S-B-

S-B-S) block copolymer having vinyl content ranging from about 10 wt% to about 50 wt% sold under the trade designation SR-8272 and SR-8273 by Firestone.

The amount of the vinyl modified block copolymer employed may depend to some extent on the targeted end-use. Typically, the adhesive composition comprises from
5 about 10 wt% to about 50 wt%, preferably from about 10 wt% to about 40 wt%, more preferably from about 10 wt% to about 30 wt% and even more preferably, from about 15 wt% to about 25 wt% of the vinyl modified block copolymer, based on the total weight of the composition.

The radiation curable adhesive composition of the invention also comprises at
10 least one tackifier, i.e., any of the ingredients described below that are useful to shift the glass transition temperature (T_g) of the vinyl modified block copolymer to a higher temperature and impart tack to the adhesive composition. Tack is defined in ASTM D-1878-61T as "the property of a material that enables it to form a bond of measurable strength immediately on contact with another surface". The amount of tackifier ranges
15 from about 10 wt% to about 90 wt%, preferably, from about 10 wt% to about 80 wt%, based on the total weight of the adhesive composition. Preferably, the adhesive composition comprises at least about 20 wt%, more preferably, at least about 40 wt%, and most preferably, at least about 50 wt% tackifier.

In general, useful tackifiers are either derived from renewable resources such as
20 rosin derivatives including wood rosin, tall oil, gum rosin as well as rosin esters and natural and synthetic terpenes, and derivatives of such; or are petroleum based resins such as hydrocarbon resins. Examples of useful hydrocarbon resins includes alpha-methyl styrene and other styrenic monomer based resins, branched and unbranched C₅ resins, C₉ resins, dicyclopentadiene (DCPD) based resins, as well as styrenic and
25 hydrogenated modifications of such. Useful tackifiers typically range from being a liquid at about 25°C (room temperature) to having a ring and ball softening point of up to about 150°C.

Preferably, the adhesive composition of the invention comprises at least one tackifier that is compatible with the polydiene block. The tackifiers are preferably rosin
30 derivatives, particularly hydrogenated rosin based tackifiers and hydrogenated styrenated terpene resins.

Useful commercially available tackifiers include, for example, Regalite® R 91, Regalite® R R101, Regalite® R S100, Regalite® R S260, Regalrez® 1018, Regalrez® Regalrez® 3102, Regalrez® 6108, Regalrez® 5095, Zonatac® Lite series such as Zonatac® 105 Lite, Escorez® 5300 series, Foral® AX, Foral® 85 and Foral® 105.

5 Optionally, the adhesive composition of the invention comprises at least one plasticizer.

 Preferably, for adhesive compositions that can be applied at low application temperatures, adhesive compositions exhibiting good cold temperature such as chill-grade or freezer-grade adhesives), and adhesive compositions exhibiting good adhesion
10 to wet surfaces, the adhesive composition comprises at least one plasticizer that is compatible with polyvinyl aromatic block, known as polyvinyl aromatic block plasticizer. The vinyl aromatic block plasticizer has the function of diluting or softening the polyvinyl aromatic block in the vinyl modified block copolymer. The useful polyvinyl aromatic block plasticizers have a softening point of less than about 100°C,
15 preferably less than about 80°C, more preferably less than about 50°C, and most preferably less than about 25°C. Also, the polyvinyl aromatic block plasticizers are typically low in molecular weight, preferably having a weight average molecular weight of less than about 3,000 g/mol, more preferably less than about 2,000 g/mol, and most preferably less than about 1,000 g/mol.

20 Useful commercially available polyvinyl aromatic block plasticizers include, such as Piccolastic® A5 from Hercules, which has a Ring and Ball softening point of 5°C and a weight average molecular weight (Mw) of 430 g/mol, and Kristalex® 3070, which has a Ring and Ball softening point of 70°C and a weight average molecular weight (Mw) of 880 g/mol from Hercules.

25 The amount of polyvinyl aromatic block plasticizers used in the adhesive composition of the invention is, preferably, up to 40 wt%, more preferable, from about 10 wt% to about 40 wt%, more preferably, from about 15 wt% to about 35wt%, based on the total weight of the composition.

 Alternatively, or in addition to the polyvinyl aromatic block compatible
30 plasticizer, the adhesive compositions of the invention may comprise one or more polydiene compatible plasticizers, at an amount up to about 60 wt%, preferably from

about 10 wt% to about 40 wt%. The polydiene compatible plasticizers are plasticizers that are more compatible with the polydiene midblock than with the polyvinyl aromatic endblock of the vinyl modified block copolymer.

Exemplary polydiene compatible plasticizers include hydrocarbon oils, polybutene, and liquid elastomers such as liquid polyisoprene. Hydrocarbon oils are primarily those hydrocarbon oils that are low in aromatic content and are paraffinic or naphthenic in character. Preferably, these oils are low in volatility, transparent and have as little color and odor as possible. The use of plasticizers in this invention also contemplates the use of olefin oligomers, low molecular weight polymers, natural oils such as vegetable oils and their derivatives and similar plasticizing liquids. Commercially available preferred polydiene plasticizers include Isolene® 40, Isolene® 75, and Isolene® 400 from Elementis Specialty.

Depending on the intended end use, the adhesive composition of the invention may further comprise at least one second polymer in combination with the block copolymer having vinyl functionality, i.e., vinyl modified block copolymer. The second polymer may serve, in some instances, as an extender to minimize the concentration of vinyl functionality containing block copolymer to reduce the cost. In other instances, however, the second polymer is an essential ingredient that contributes synergistic adhesive properties such as improved tack in combination with high heat resistance. The second polymer is typically employed at concentrations up to about 40 wt%, preferably from about 5 wt% to about 40 wt%, and more preferably, from about 5 wt% to about 20 wt%, based on the total weight of the composition.

A wide variety of polymers may be employed as the second polymer. The second polymer is typically a second block copolymer that does not have vinyl functionality, i.e., a block copolymer that has not been 1,2-vinyl modified, a homogeneous ethylene/alpha-olefin interpolymers, an amorphous polyalphaolefin, an interpolymers of ethylene, or mixtures thereof. These polymers may be relatively insensitive to radiation curing but offer dilution or synergistic effects on adhesive properties.

A wide variety of the second block copolymers, which have not been vinyl modified, useful as a second polymer in the radiation curable adhesive composition of the invention include A-B-A triblock structures, A-B diblock structures, (A-B)_n radial

block copolymer structures, as well as branched and grafted versions of such, wherein the A block is a non-elastomeric polymer block, typically comprising polystyrene and/or vinyl aromatic structure and the B block is an unsaturated conjugated diene or hydrogenated version thereof. In general, the B block is typically isoprene, butadiene, ethylene/butylene, ethylene/propylene, and mixtures thereof.

Useful commercially available second block copolymers include the Kraton® D and G series block copolymers from Shell Chemical Company (Houston, TX), Europrene® Sol T block copolymers from EniChem (Houston, TX), Vector® block copolymers from Exxon (Dexco) (Houston, TX), as well as others.

The inventors have found that by blending at least one styrene-isoprene-styrene (SIS) block copolymer having a styrene content of less than about 25 wt% as a second block copolymer together with the vinyl modified block copolymer, the resultant adhesive composition exhibits improved tack while maintaining the high shear adhesive failure temperature (SAFT).

A homogeneous ethylene/ α -olefin interpolpolymer is a homogenous linear or substantially linear interpolpolymer of ethylene and at least one C₃-C₂₀ α -olefin. The term "interpolpolymer" is used herein to indicate a copolymer, terpolpolymer, or a higher order polymer. That is, at least one other comonomer, such as, in the case of ethylene/ α -olefin interpolpolymer, at least one C₃-C₂₀ α -olefin comonomer, is polymerized with ethylene to make the interpolpolymer. The term "homogeneous" means that any comonomer is randomly distributed within a given interpolpolymer molecule and substantially all of the interpolpolymer molecules have the same ethylene/comonomer ratio within that interpolpolymer.

The homogeneous ethylene/ α -olefin interpolpolymer used in the preferred radiation curable adhesive compositions of the invention have a density of no greater than 0.965 g/cm³, preferably no greater than 0.900 g/cm³, more preferably no greater than 0.890 g/cm³, and even more preferably no greater than 0.885 g/cm³, and most preferably no greater than 0.880 g/cm³. In the case of the radiation curable pressure sensitive adhesive compositions, the homogeneous ethylene/ α -olefin interpolpolymers have a density of at

least 0.850 g/cm³, preferably at least 0.860 g/cm³, and more preferably about 0.870 g/cm³.

Amorphous polyalpha-olefins (APAO), also described as amorphous polyolefins, differ from homogeneous ethylene/ α -olefin interpolymers, with regard to homogeneity,
5 molecular weight distribution (M_w/M_n), as well as comonomer (α -olefin) content.

Amorphous polyalpha-olefins are homopolymers, copolymers and terpolymers of alpha-olefins which are typically polymerized by means of processes that employ Ziegler-Natta catalysts, resulting in a relatively broad molecular weight distribution, typically greater than 4. In contrast, the homogeneous ethylene/ α -olefin interpolymers are characterized
10 as having a narrow molecular weight distribution. The homogeneous ethylene/ α -olefin interpolymers have a M_w/M_n of less than 4, preferably less than 3, more preferably from 1.5 to 2.5, even more preferably from 1.8 to 2.2, and most preferably about 2.0. Further, whereas amorphous polyalpha-olefins produced from Ziegler-Natta catalysis typically have an alpha-olefin concentration greater than 50 wt%, homogeneous ethylene/ α -olefin
15 interpolymers useful in the present invention are substantially ethylene, having a much greater ethylene content than α -olefin comonomer content.

Interpolymers of ethylene are polymers of ethylene and at least one comonomer selected from the group consisting of vinyl esters of a saturated carboxylic acid wherein the acid moiety has up to 4 carbon atoms, unsaturated mono- or dicarboxylic acids
20 having 3 to 5 carbon atoms and a salt thereof, esters of the unsaturated acid derived from an alcohol having 1 to 8 carbon atoms, and mixtures thereof. Terpolymers of ethylene and these comonomers are also suitable. Particularly suitable interpolymers of ethylene are ethylene/vinyl acetate (EVA), ethylene/methyl acrylate (EMA), ethylene n-butyl acrylate (EnBA), and mixtures thereof having a relatively low comonomer content of
25 about 25 wt% or less.

The radiation curable composition of the invention may also comprise a wax.

Particularly in the case of bottle-labeling, laminating, bookbinding, and packaging adhesives, wherein pressure sensitivity is undesirable, waxes may be usefully employed in the radiation curable adhesive compositions of the invention.

30 Waxes are commonly used to modify the viscosity and reduce tack at concentrations of up to about 40 wt%, and preferably from about 10 wt% to about 40

wt%, based on the total weight of the composition. Preferred waxes are those having a minimum amount of unsaturation. Paraffin wax, such as Paraffin 155F exhibits a sufficiently low amount of UV absorbing components. Other waxes may also be useful provided that the adhesive composition is cured at a temperature above the cloud point of the wax.

In general, the additional ingredients compounded with the radiation sensitive vinyl modified block copolymers typically contain low levels of unsaturation and minimal aromatic content such that the ingredients do not adversely affect the radiation responsiveness of the adhesive composition. Further, as is known in the art, various other components can be added to modify the tack, color, odor, etc., of the radiation curable adhesive composition. Additives such as antiblock additives, pigments, and fillers, can also be included in the formulations. It is generally preferred that the additives should be relatively inert and have negligible effects upon the properties contributed by the homogeneous linear or substantially linear interpolymers, tackifying agent, and plasticizer.

In the case of UV curing, one or more photoactive initiators and/or photoactive coupling agents are added to the adhesive composition. Representative examples include, but are not limited to aldehydes, benzaldehyde, acetaldehyde, and their substituted derivatives; ketones such as acetophenone, benzophenone, and their substituted derivatives, particularly the 4-alkylbenzophenones wherein the alkyl group has 1 to 18 carbon atoms; quinones such as benzoquinone, anthraquinone, and their substitutes derivatives; thioxanthenes, such as 2-isopropylthioxanthone and 2-dodecylthioxanthone; and certain chromophore-substituted halomethyl-sym-triazines, such as 2,4-bis(trichloromethyl)-6-(3',4'-dimethoxyphenyl)-sym-triazine.

Another suitable type of photoinitiator that may be employed in the compositions of the present invention is the "alpha cleavage type" photoinitiator. This photoinitiator is particularly beneficial when other unsaturated species such as acrylated oligomers and monomers are further employed. Alpha cleavage type photoinitiators are known in the art. Commercial examples include Irgacure 184 and Darocur 1173, both available from Ciba-Giegy (Hawthorne, NY).

Preferred radical type photoinitiators include acylphosphine oxides, bisacrylphosphine oxides, and mixtures thereof, and blends in which they are included. Useful commercially available examples include Irgacure® 819, Irgacure® 1800, and Irgacure® 1850 from Ciba; and Lucirin TPO from BASF.

- 5 Photoactive initiators and photoinduced coupling agents are present at a concentration of from about 0.05 wt% to about 3 wt%, preferably from about 0.1 wt% to about 2.0 wt% and more preferably from about 0.3 wt% to about 1.5 wt%, based on the total weight of the composition for UV curable compositions. However, in the case of electron-beam (EB) radiation curing, photoactive agents are not needed to crosslink the
10 block copolymer having vinyl functionality.

- To cure the composition of the invention, a source of actinic radiation of sufficient energy (i.e., wavelength ranges) to generate free radicals when incident upon the particular photoinitiator selected for use in composition should be chosen. The preferred wavelength ranges for the photoinitiators disclosed above is 400 to 250 nm.
- 15 The amount of radiant energy density desired to crosslink the adhesive film or coating formed from the composition of the invention is from about 25 to about 200 mJ/cm², (for UVA, from about 315 nm to about 400 nm), more preferably from about 40 to about 200 mJ/cm², (for UVA, from about 315 nm to about 400 nm), as measured with a Power-Puck™ radiometer manufactured by EIT. Details of the photocure process are disclosed
20 in U.S. Patent Nos. 4,181,752 and 4,329,384, incorporated herein by reference.

- The compositions of the invention can also be cured by means of electron-beam (EB) radiation without using photoinitiators. The dosage needed to crosslink the compositions vary depending on the particular composition but generally ranges from about 1 to about 20 Mrads, preferably from about 2 to about 10 Mrads. Details of
25 suitable processes for electron-beam (EB) curing of adhesives-coated substrates can be found in U.S. Patent No. 4,533,566, which is incorporated herein by reference.

- The radiant energy density and thus, the line speed for sufficient curing is dependent on the composition and more importantly the thickness of the adhesive film being cured. For about 1 mil adhesive films, the adhesive compositions are sufficiently
30 cured at line speeds ranging from about 300 ft/min to about 500 ft/min when curing with 2x600 w lamps.

Depending on the kinds and amounts of ingredients that are combined with the block copolymer having vinyl functionality, the resultant adhesive composition exhibits at least one of a variety of improved properties. In some embodiments, the adhesive composition advantageously has the Brookfield viscosity of less than about 10,000 cps at about 160°C, preferably less than about 8,000 cps at about 160°C, more preferably less than about 6,000 cps at about 160°C, and even more preferably, less than about 4,000 cps at about 160°C, that allows the adhesive composition applied at a low application temperature, i.e., an application temperature of no greater than about 150° C, preferably, no greater than about 140° C and more preferably, no greater than about 130° C. The adhesive composition applied at low application temperature may be characteristically described as a "warm melt" adhesive since the composition exhibits a low viscosity at even lower temperatures. Hence, the composition exhibits the desired viscosity at a temperature of less than about 140°C, and preferably at a temperature of less than about 130°C. In the most preferred embodiments, the adhesive composition is sufficiently fluid at about 120°C. The low application temperature is amenable to coating to heat sensitive substrates, such as low gauge polyethylene film. The low application temperature also aids in preventing thermal degradation of the adhesive composition.

The adhesive compositions of the invention can be formulated such that the compositions exhibit improved plasticizer resistance, sufficient tack and improved heat resistance. Preferably, the shear adhesion failure temperature (SAFT) is no less than about 300°F, and more preferably, no less than about 350°F, and the static shear is no less than about 24 hours after curing of the adhesive composition. In the case of pressure sensitive adhesives, the high heat resistance as indicated by high SAFT is coupled with sufficient tack, depending on the end use intended. The Loop Tack is typically at least about 30 oz/in (1.875 lb/in), preferably about 50 oz/in (3.125 lb/in) or greater, and more preferably, about 75 oz/in (4.6 lb/in) or greater. For permanent grade pressure sensitive adhesives, the 180° Peel value is typically at least about 2.5 lbs/ linear inch (pli), preferably at least about 3.0 lbs/ linear inch (pli), and more preferably at least about 4 lbs/ linear inch (pli) or greater depending on the intended end use.

The adhesive composition exhibits good plasticizer resistance and solvent resistance. The plasticizer resistance is particularly advantageous for bonding highly

plasticizer substrates such as various oil extended elastomers based substrates. The compositions are also resistant to exposure to oil based skin care products that may be incorporated in disposable absorbent products.

5 The adhesive may be bonded to a variety of substrates such as various films, nonwovens, paperstock, paperboard, plastics, metals, painted substrates, glass, leather, rubber, etc.

10 The adhesive compositions of the invention can be used for various applications including for use as pressure sensitive adhesives for high performance tapes and labels, and particularly for automotive applications such as window labels and license plate tabs, sterilizable medical applications, freezer-grade labels, shrinkable label for contoured containers, hook and loop tapes, abrasive products, road marking tapes, foam bonding, bonding rubber gaskets to air filters and positioning adhesives. Further, both pressure sensitive as well as non-pressure sensitive adhesive compositions can be employed for film laminating and nonwoven construction applications such as disposable diaper
15 construction as well as for wood flooring adhesives. Further, the adhesive compositions are low in odor.

In another aspect, the invention is directed to a double-faced tape and a method of producing the same. The double-faced tape is formed from a single layer of the adhesive composition of the invention. It comprises a first surface and a second opposing surface
20 without having any supporting substrate in between the two surfaces. Upon radiation cure the first surface exhibits a first 180° peel value and a second opposing surface exhibits a second 180° peel value that is greater than the first peel value. Preferably, the ratio of the second peel value to the first peel value is from about 2:1 to about 20:1, more preferably, from about 4:1 to about 20:1.

25 According to the invention, the double-faced tape is prepared by applying a radiation curable adhesive composition of the invention onto a release-coated surface to obtain an adhesive film having a first surface and a second opposing surface that is disposed on the release-coated surface; and curing said adhesive film by exposing the first surface of it to radiant energy to obtain a double-faced tape, of which the two
30 surfaces exhibit differential adhesion. It is believed, but not bound by any theory, that curing the adhesive film to a different extent on the first surface of the adhesive layer in

comparison to the second opposing surface of the same adhesive layer creates the differential adhesion. The differential adhesion properties obtained depend on the thickness of the adhesive layer, radiation cure conditions such as line speed and lamp output.

5 The thickness of the adhesive film is typically at least about 3 mils and preferably, from about 4 to 10 mils. The adhesive composition is compounded in such a manner that the radiant energy, such as the light in the case of UV cure, does not uniformly penetrate the adhesive film through the entire thickness. Thus, the adhesive surface closer to the radiant energy source tends to crosslink to a much greater extent
10 than the opposing surface of the adhesive film further from the radiant energy source. Upon cure by means of radiation, the first surface of the adhesive film exhibits removable-grade adhesive characteristics and the second opposing surface exhibits permanent-grade adhesive characteristics. The peel value of the permanent-grade adhesive surface is typically at least two times that of the opposing adhesive surface and
15 preferably 4 to 20 times greater.

 The applicants have also discovered that the compositions of the invention, particularly the compositions comprising at least one polyvinyl aromatic block plasticizer exhibit excellent adhesion to wet surfaces in addition to maintaining good adhesion properties throughout a temperature range from about 0°C to about 100°C. Such
20 properties are amenable to be utilized in a plastic wrap product comprising a film layer and a releasably sealable adhesive such as set forth in U.S. Patent No. 5,662,758, incorporated herein by reference. Good adhesion to wet surfaces and stable adhesive properties without transfer are also important characteristics for medical grade adhesives that are bonded to skin.

25 The invention is further illustrated by the following non-limiting examples. It should be understood, however, that many variations and modifications may be made while remaining within the scope of the present invention. All the ingredients are in percentage by weight unless otherwise stated. The shear adhesion failure temperatures (SAFT) were tested according to the SAFT Testing Method I unless otherwise stated.

30

Examples

Test Methods

Brookfield Viscosity

- 5 Brookfield viscosity is measured with a Brookfield RVDT Viscometer in accordance with the manufacturer's operating instructions.

Peel Testing

- 10 Peel value is measured in accordance with PSTC-1, revised 8/85, "Peel Adhesion of Single Coated Pressure-Sensitive Tapes at 180° Angle". The adhesive is coated at a temperature of 350°F (177°C) onto 2 mil Mylar™ (polyethylene terephthalate) at the coating thickness of 1 mil. The coated Mylar™ is cut into strips of 1 inch in width by 6 inches in length (2.5 cm by 15.2 cm). The strips is then adhered to stainless steel plates, reporting the average peel value of four (4) samples at room temperature (25°C).

15

Static Shear

- 20 Static shear is measure in accordance with PSTC-7, revised 8/85, "Holding Power of Pressure Sensitive Tapes". 1 "x1 " samples are coated in the same manner as described in the Peel Testing. The samples are laminated onto a stainless steel test panel with a 4.5 pound (2.0 kg) hand roller and allowed to dwell for 20 minutes prior to testing. A 500 g load is employed, reporting the average static shear of four (4) samples and the failure mode at temperature indicated.

25 Loop Tack

Loop tack is measured in accordance with FINAT Test Method No. 9 (FTM 9)

The samples are coated in the same manner as described in the Peel Testing. The samples are adhered to stainless steel at room temperature, reporting the average loop tack value of five (5) samples and the failure mode.

30

Rheology Testing

The storage modulus (G') and tan delta are determined in accordance with ASTM D4440-93. A test frequency of 10 radians/sec and a temperature ramp or step test is performed with a 10 mm diameter parallel plate test geometry with a gap of 1 to 4 mm.

5 Shear Adhesion Failure Temperature (SAFT) Test Method I

The 1 "x1 " adhesive film on 2 mil Mylar™ (polyethylene terephthalate) substrate is placed on a solvent cleaned stainless steel panel and rolled down with a standard 4.5 lb roller. The sample sat for 30 minutes at 73° F/50% relative humidity and then, is placed in a 200° F oven. A 500 gram weight is suspended from each sample. After one minute
10 equilibration, the timer is started and the oven temperature is increased at a rate of 1° F per minute to a final temperature of 350° F, reporting the average failure temperature of four (4) samples.

Shear Adhesion Failure Temperature (SAFT) Test Method II

15 A first 12 " long sheet of Mylar™ is taped to a heavy chip board. Two pieces of release paper are taped onto the Mylar™ parallel to each other, one inch apart. A second 12 " long sheet of Mylar™ is taped on top of the first Mylar™ containing release paper. The second Mylar™ sheet is folded backward. Sandwich the second sheet of Mylar™
20 between two glass rods, having the front glass rod equipped with two pieces of masking tape wrapped around it. This will achieve a desired film thickness of adhesive when the adhesive is spread with the glass rod. A puddle of adhesive is poured onto the first sheet of Mylar™ between two release paper. The glass rods are pulled to spread the adhesive in a consistent film and mate the second sheet of Mylar™ to the first sheet thus forming a bond. The resultant bond is about 1 "x12 ". This is then cut into 12 pieces as samples,
25 each containing a 1 "x1 " bonded area. The samples are conditioned in an oven at 130°F for approximately 5 minutes and then exposed to UV radiation. Intensity of radiation is recorded. The samples are turned over and the conditioning and UV radiation are repeated to ensure adequate curing through the adhesive film. The samples are then placed in an oven with a 500gram weight applied in shear mode. The oven temperature
30 increases at 25°C/hour. The temperature at which failure occurred is recorded, reporting the average failure temperature of four (4) samples.

Peel Adhesion Failure Temperature (PAFT)

A first 12" long sheet of Mylar™ is taped to a heavy chip board. Two pieces of release paper are taped onto the Mylar™ parallel to each other, one inch apart. A second 12" long sheet of Mylar™ is taped on top of the first Mylar™ containing release paper. The second Mylar™ sheet is folded backward. Sandwich the second sheet of Mylar™ between two glass rods, having the front glass rod equipped with two pieces of masking tape wrapped around it. This will achieve a desired film thickness of adhesive when the adhesive is spread with the glass rod. A puddle of adhesive is poured onto the first sheet of Mylar™ between two release paper. The glass rods are pulled to spread the adhesive in a consistent film and mate the second sheet of Mylar™ to the first sheet thus forming a bond. The resultant bond is about 1"x12". This is then cut into 12 pieces as samples, each containing a 1"x1" bonded area. The samples are conditioned in an oven at 130°F for approximately 5 minutes and then exposed to UV radiation. Intensity of radiation is recorded. The samples are turned over and the conditioning and UV radiation are repeated to ensure adequate curing through the adhesive film. The samples are then placed in an oven with a 100gram weight applied in peel mode. The oven temperature increased at 25°C/hour. The temperature at which failure occurred is recorded, reporting the average failure temperature of four (4) samples.

Examples

The ingredients employed in the examples are listed in the following Table A

Table A

25

<u>Tradename</u>	<u>Chemical Description</u>	<u>Supplier</u>
Kraton D KX-222CS	18% styrene SB ₂ B ₂ , 53%-63% vinyl butadiene	Shell
SR-8272	22% styrene, 10% vinyl butadiene, 12 MI	Firestone
	Linear multiblock S-B-S block copolymer	
SR-8273	22% styrene, 47% vinyl butadiene, 12 MI	Firestone

30

		Linear multiblock S-B-S block copolymer	
	Piccolastic A-5	5°C styrenic monomer based endblock plasticizer	Hercules
	Kaydol Oil	white mineral oil midblock plasticizer	Witco
	ECR-149-B	85°C hydrogenated aromatic midblock resin	Exxon
5	Regalrez 1094	94°C hydrogenated aromatic midblock resin	Hercules
	Regalrez 1018	94°C hydrogenated aromatic midblock resin	Hercules
	Foral AX	68°C hydrogenated rosin acid tackifying resin	Hercules
	Zonatac 105	105°C hydrogenated styrenated terpene resin	Arizona
	Septon 2043	13% styrene, 14 MFR (200°C/10 kg) SEPS	Kuraray
10	Kraton G-1657	13% styrene, 35% diblock, 8 MI S-EB-S	Shell
	Kraton G-1780	6 % styrene S-EB-S block copolymer	Shell
	Kraton G-1651	33% styrene, 100% triblock S-EB-S block copolymer	Shell
15	Kraton G-1650	29% styrene, 100% triblock S-EB-S block copolymer	Shell
	Kraton G-1726	30% styrene, 70% diblock, 65 MI SEBS	Shell
	Kraton D-1119	22% styrene, 65% diblock SIS	Shell
	Kraton D-1111	22% styrene, 3 MI Linear SIS	Shell
	Rextac 2715	1500 mpas 110°C butene-1 copolymer	Rexene
20	Affinity SM-8400	.870 g/cm ³ , 30 MI EO homogeneous interpolymers	Dow
	.870 g/cm ³ /1000 MI	ethylene-octene homogeneous interpolymers	Dow
	.858 g/cm ³ /30 MI	ethylene-octene homogeneous interpolymers	Dow
	Irganox 1010	hindered phenolic antioxidant	CibaGiegy
	Irganox 3052 FF	2-propanionic acid radical scavenger	CibaGiegy
25	Irgafos 168	phosphite cosynergist antioxidant	CibaGiegy
	Irgacure 819	photoinitiator	CibaGiegy
	Irgacure 651	photoinitiator	CibaGiegy
	Isolene 40-S	40,000 Mw, 360-550 poise at 38°C polyisoprene	Elementis
	Sumilizer GS	2-[1-(2-hydroxy-3, 5-di-tert-pentylphenyl)	Sumitomo
30		ethyl]-4, 6-di-tert pentylphenyl acrylate antioxidant	
	Sumilizer TP-D	pentaerythrityl tetrakis-(3-dodecylthiopropionate)	Sumitomo

	antioxidant	
	Sylvalac ZT 105 LT styrenated terpene tackifier	Arizona
	Regalite R-101 100° C hydrogenated aromatic midblock resin	Hercules
	Kristalex 3070 70° C pure monomer endblock plasticizer	Hercules
5	WAX Paraffin 155° F 155° F melt point paraffin wax	Bareco

Examples 1-5

Adhesive compositions were prepared by combining the ingredients according to Table I. In addition to the listed ingredients, the compositions also contained 0.3 wt% each of Irganox 1010, Irganox 3052 FF and Irgafos 168 antioxidants and 0.8 wt% of Irgacure 819 photoinitiator, except for the composition of Example 3 that contained 0.4 Sumilizer GS and 0.5 Sumilizer TP-D as alternative antioxidants. The Brookfield viscosities of the compositions were tested and the data are listed in Table II.

A 1 mil coating of the composition of Example 1 was applied onto a Mylar™ (polyethylene terephthalate) film, then cured by exposure to 7.5 Mrad of electronic beam (EB).

The 180° Peel value tested before cure and after cure showed an increase of from 0.9 lbs/in (pre-cure) to 1.2 lbs/in (after cure). The radiation induced crosslinking eliminated the cohesive failure tendencies.

The adhesive compositions of Examples 2-5 were applied to Mylar™ (polyethylene terephthalate) films and cured by exposing to a 600 watt H bulb lamp at 50 feet per minute. SAFT, 180 peel values and loop tack were tested and the data are listed in Table III.

Table I

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Ex. 5
KX-222CS	12.0	19.8	19.8	19.7	24.6
Piccolastic A-5	12.0	19.5	--	19.7	9.8
Kristalex 3070	--	--	19.5	--	--

Regalrez 1018	74.4	36.9	36.9	58.9	54.1
Foral AX	--	22.1	--	--	9.8
ECR-149B	--	--	22.1	--	--

Table II Brookfield viscosity (cps)

5		Ex. 1	Ex. 2	Ex. 3	Ex. 4	Ex. 5
	Visc. at 160°C	385	1,950	3,850	640	4,200
	Visc. at 300°F			5,400		
	Visc. at 250°F	2165		18,800		
	Visc. at 200°F	4120	22,000*	112,000		

10

* Visc. at 100°C

Table III Adhesive Properties

15

		Ex. 2	Ex. 3	Ex. 4	Ex. 5
	180° Peel (lbs/in)	2.5	--	0.8	1.1
	Loop Tack (lb/in)	6.25	2.5	3.6	1.2
	SAFT (°F)	>350	>350	>350	>350
20	Static Shear (at 100°C)	> 24 hours	--	--	--

Examples 1-5 represent low application temperature pressure sensitive adhesives that can advantageously be applied as low as 200°F. Example 2 also advantageously has very high initial tack. In addition, the composition of example 2 was also tested for

25 adhesion on Pyrex glass substrate. The 180° peel values on dry and wet Pyrex glass substrates were 3.9 lb/in and 1.2 lb/in, respectively, at a coat weight of 12.5 grams, according to the Peel Testing Method with the exception of using a Pyrex glass plate

instead of a stainless steel plate. It is shown that the composition exhibits high peel value to low energy surfaces, particularly wet surfaces,

Example 6

5 An adhesive composition is prepared by combining 30 parts KX-222C, 52.9 parts ECR-149-B, 14.2 parts Kaydol Oil, 1 part Sumilizer GS, 1 part Sumilizer TPD and 0.9 parts Irgarcure 819. The Brookfield viscosity, 180° peel value, loop tack, SAFT and static shear of the composition was tested and the data are listed in Table IV.

10 A 10 mil thick adhesive film of the composition was coated onto release paper and cured at 60 feet per minute (fpm) by exposing to a 600 watt H bulb lamp from Fusion to obtain a double-faced tape. The 180° peel values on both surfaces of the double-faced tape were tested and the data is listed in Table V.

Table IV

15

Brookfield Viscosity (cps)

	at 275°F	63,000
	at 300°F	33,063
	at 325°F	18,750
20	at 350°F	11,600
	180° Peel	4.0 lbs/in
	Loop Tack	30 oz/in
	SAFT	>350°F
	Static Shear (at 100°C)	> 24 hours

25

Example 7

 An adhesive composition was prepared according to Example 6, except using SR-8273 instead of KX-222C and 1.9 parts Irgarcure 819 instead of 0.9 parts Irgarcure 819.

30 The samples were coated onto release paper at 4.0 mils adhesive thickness and then cured at 100 and 300 feet per minute (fpm), respectively, by exposing to a 600 watt

H bulb lamp. The 180° peel values on both surfaces of the double-faced tape samples were tested and the data is listed in Table V.

Table V 180° Peel Values of the Double-faced Tape

5

	Ex. 6	Ex. 7-A (cured at 100fpm)	Ex. 7-B (cured at 300 fpm)
First Surface	0.1 pli, 100% AF	1.565 pli	1.840 pli
Second Surface	7.54 pli, 100% AF	5.824 pli	6.334 pli

As shown in Table V, the double-faced tape of the invention exhibited different adhesion levels on opposing surfaces of the adhesive film due to differential curing of the adhesive film formed from the single composition. The adhesive composition is particularly useful for the tape market to create a transfer tape having differential adhesion employing a single adhesive composition in the absence of a backing. Traditionally, a double-faced tape is made by coating a permanent grade adhesive on one surface of a Mylar™ backing film and a removable grade adhesive on the opposite surface of the backing film.

15

Examples 8-19

Adhesive compositions were prepared by combining the ingredients according to Table VII and Table VIII. SAFT, 180 peel values and loop tack were tested and the data are listed in Table IX.

20

Examples 8-10 demonstrate that random multiblock styrene-butadiene-styrene (SBS) block copolymers having either low vinyl or high vinyl functionality are radiation curable. Examples 11-16 exemplify adhesive compositions having improved heat resistance. These examples also demonstrate that blends of the vinyl functionalized block copolymer in combination with homogeneous ethylene/alpha-olefin interpolymers resulted in the highest SAFT values in combination with improved peel and loop tacks.

25

Examples 18 and 19 relative to Example 17 demonstrates that blends of the vinyl functionalized block copolymer in combination with styrene-isoprene-styrene (SIS) increases the peel and loop tack without compromising the heat resistance.

5

Table VII

	Ex. 8	Ex. 9	Ex. 10	Ex. 11	Ex. 12	Ex. 13
KX-222C	30			20	20	20
SR-8273		30				
SR-8272			30			
Affinity SM-8400				10		
.870 g/cm ³ /1000 MI					10	
Rextac 2715						10
Zonatac 105	52.9	52.9	52.9	52.9	52.9	52.9
Kaydol Oil	14.2	14.2	14.2	14.2	14.2	14.2
Sumulizer GS	1	1	1	1	1	1
Sumulizer TP-D	1	1	1	1	1	1
Irgacure 819	0.9	0.9	0.9	0.9	0.9	0.9

Table VIII

10

	Ex. 14	Ex. 15	Ex. 16	Ex. 17	Ex. 18	Ex. 19
KX-222C	20	20	20	40	20	20
Kraton G-1780	5					
Kraton G-1650		5				
Kraton G-1726			10			
Kraton D-1119					20	
Kraton D-1111						20
Zonatac 105	55.4	55.4	52.9	47.9	47.9	47.9
Kaydol Oil	16.7	16.7	14.2	9.2	9.2	9.2
Sumulizer GS	1	1	1	1	1	1
Sumulizer TP-D	1	1	1	1	1	1
Irgacure 819	0.9	0.9	0.9	0.9	0.9	0.9

Table IX

Ex. No.	SAFT (°F) (uncured)	SAFT (°F) (cured)	180° Peel Value (pli)	Loop Tack (lbs./in ²)
Ex. 8	174	>350	4.1, 100% AF*	1.25
Ex. 9	141.5	>350	3.1, 90% AF*,	
Ex. 10	126	>335-350	3.5, 100% AF*	
Ex. 11	147.5	>350	5.4, 100% AF*	4.0
Ex. 12	138	>350	5.0, 100% AF*	1.9
Ex. 13	132.5	186	5.7, 30% CF*	1.7
Ex. 14	151	>350	4.5 100% AF*	
Ex. 15	162	>350	4.5, 100% AF*	2.1
Ex. 16	162	330	4.3	1.8
Ex. 17	201	350	3.4, 100% AF*	2.8
Ex. 18	188	350	3.6, 100% AF*	2.6
Ex. 19	193	>350	5.0, 100% AF*	4.2

5 AF*: adhesive failure, i.e., the adhesive remains on the Mylar™ substrate.

CF*: cohesive failure, i.e., failure due to separation within the adhesive layer, resulting in a significant amount of adhesive left on the Mylar™ substrate and the stainless steel test panel.

Example 20

An adhesive composition was prepared by combining the ingredients according to Table X. A 10 mil thick adhesive film of the composition was coated onto a loop
5 substrate and cured at 60 feet per minute (fpm) by exposing to a 600 watt H bulb lamp from Fusion. 180° peel value, SAFT, loop tack and static shear were tested and the data is listed in Table X.

Table X

10

KX-222C	21.2
ECR-149-B	51.3
Kaydol Oil	5.0
Isolene 40-S	20
15 Sumilizer GS	1.0
Sumilizer TP-D	1.0
Irgacure 819	0.5

Adhesive Properties

20 180° Peel (lbs/in)	4.4
Loop Tack (oz/in)	45
SAFT (°F)	>350
Static Shear (at 100°C) (hr)	> 24

25

Example 21

An adhesive composition was prepared by combining the ingredients according to Table XI. The composition obtained had an initial Brookfield viscosity of 380 cps at 300°F and 385 cps at 325° F. Thermostability was confirmed by monitoring viscosity at
30 application temperature of 325° F over 24 hours. The viscosity remained 385 cps.

Table XI

	KX-222CS	15
5	Irganox 1010	0.23
	Irganox 3052 FF	0.23
	Irgafos 168	0.23
	Regalrez 1018	27.7
	ECR-149B	16.5
10	Piccolastic A5	15.0
	Paraffin 155F	24.6
	Irgacure 819	0.6

15 The adhesive composition was coated onto a Mylar™ film at about 1.0-1.5 mil thickness and cured with a 600 W/inch H bulb at 70 feet per minute. SAFT tested on the 1 "x1 " overlap adhesive to Mylar™ was greater than 350° F.

The adhesive composition was also coated onto a standard coated 3 "x 9 " paper label stock at about 1.0-1.5 mil and the performance was evaluated and reported as follows:

20

	Before Cure	After Cure
Pick-up bond evaluation to glass	Fiber Tear	Fiber Tear
Overlap bond evaluation	Fiber Tear	Fiber Tear

The adhesive composition was also coated onto an oriented polypropylene (OPP) 2 mil film label at about 1.0 mil. then, bonded to the front side of a second piece of label stock and cured through the clear overlap at 100 fpm with a 600 W/inch H bulb. This simulates the overlap portion of a typical roll-fed label. SAFT tested on the

5 1"x1" overlap adhesive to OPP was about 190° F. Overlap bond evaluation showed strong substrate deformation.

As shown by the above properties, the adhesive composition is a low viscosity hot-melt adhesive designed for adhering labels to containers such as plastic and glass containers. The high SAFT value confirms the excellent performance under stress and
10 heat necessary to allow the filmic label to shrink under exposure to heat keeping the seam tight. In this way the label can conform to the size and shape of the container. The cured adhesive exhibiting high heat resistance is recommended for shrink-labeling.

Examples 22-24

15 Adhesive compositions of Examples 22-24 were prepared by combining the ingredients according to the following Table XII. The compositions were then tested according to the PAFT Testing Method and the SAFT Testing Method II. The data is listed in Table XIII.

20

Table XII

Ingredients	Ex. 22	Ex. 23	Ex. 24
KX-222C	21	28	31
Isolene 40	15	8	5
P. Wax 155	25	25	25
Zonatack 105 LT	37.37	37.16	37.07
Sumulizer GS	0.5	0.5	0.5

Sumulizer TP-D	0.5	0.5	0.5
Irgacure 819	0.63	0.84	0.93

Table XIII

Ex. No.	Brookfield Viscosity (cps)	Film thickness (mil)	PAFT (°F)	SAFT(°F)
22	6280 (300°F)	7	132	>350
	2100 (350°F)	11	135	275 ³
23	5450 (350°F)	10-13	128 ¹	339 ⁴
24	9360 (350°F)	13-18	127 ²	304 ⁵

5

1. Average of 9 samples; 2. Average of 8 samples; 3. Average of 5 samples; 4. Average of 10 samples; 5. Average of 7 samples.

Examples 22-24 represent non-pressure sensitive adhesive compositions that are useful for casemaking application as a replacement for animal glue. The compositions are also useful for other bookbinding applications, particularly one-shot bookbinding, as well as various packaging applications. The compositions maintain sufficient tack after exposure to UV light to mate the adhesives to book cover materials and obtain good adhesion. The tack is lost as the adhesive sets. The adhesives have outstanding SAFT with moderate PAFT. They also have excellent flexibility. This flexibility would provide good layflat characteristics that are important in one-shot bookbinding.

What is claimed are:

1. A radiation curable adhesive composition applied at a low application
5 temperature comprising:
 - a) from about 10 wt% to about 40 wt% of at least one block copolymer having at least two blocks wherein the first block is polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality;
 - b) from about 0 wt% to about 20 wt% of a second polymer; and
 - 10 c) from about 10 wt% to about 90 wt% of at least one tackifier;said adhesive composition having a viscosity of less than 6,000 cps at the temperature of 160°C.
2. The adhesive composition according to claim 1, wherein said adhesive crosslinks
15 through said vinyl functionality upon exposure to radiant energy.
3. The adhesive composition according to one of claims 1 and 2, wherein the total content of the block copolymer and the second polymer is at least about 15 wt%, based on the total weight of the composition.
- 20 4. The adhesive composition according to any one of claims 1-3, wherein said tackifier is a polydiene compatible tackifier.
5. The adhesive composition according to any one of claims 1- 4, further comprising
25 a polyvinyl aromatic block compatible plasticizer.
6. The adhesive composition according to any one of claims 1-5, wherein from about 30 wt% to about 90 wt% of the ingredients composed of the composition is liquid at ambient temperature.

7. The adhesive composition according to any one of claims 1-6, wherein said adhesive composition exhibits a loop tack of greater than 3 lb/in and a shear adhesion failure temperature of at least 300°F.
- 5 8. The adhesive composition of claim 7, wherein said adhesive composition exhibits a loop tack of greater than 4.6 lb/in.
9. The adhesive composition according to any one of claims 1-8, wherein said adhesive composition has a viscosity of less than 6,000 cps at a temperature of 140°C.
- 10 10. A radiation curable adhesive composition comprising:
- a) from about 10 wt% to about 40 wt% of at least one block copolymer having at least two blocks wherein the first block is a polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality;
- 15 b) from about 10 wt-% to about 80 wt-% of least one tackifier that is compatible with the polydiene block; and
- c) from about 10 wt% to about 40 wt% of at least one plasticizer selected from the group consisting of polyvinyl aromatic block compatible plasticizers having softening point of no greater than 100° C, polydiene compatible plasticizers having a weight
- 20 average molecular weight of no less than 20,000, and the combinations thereof.
11. The adhesive composition according to claim 10, wherein said polyvinyl aromatic block compatible plasticizers have a softening point of less than about 80°C.
- 25 12. The adhesive composition according to one of claims 10 and 11, wherein said polyvinyl aromatic block compatible plasticizers have a softening point of less than about 50°C.
13. The adhesive composition according to any one of claims 10-12, wherein said
- 30 polyvinyl aromatic block compatible plasticizers have a softening point of less than about 25°C.

14. The adhesive composition according to any one of claims 10-13, wherein said polydiene compatible plasticizers having a weight average molecular weight of from about 20,000 to about 100,000.

5 15. A radiation curable adhesive composition comprising:

a) from about 10 wt% to about 40 wt% of at least one block copolymer having at least two blocks wherein the first block is a polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality;

10 b) from about 5 wt% to about 40 wt% of at least one second polymer selected from the group consisting of styrenic block copolymers, ethylene/ α -olefin interpolymers, interpolymers of ethylene, and mixtures thereof; and

c) from about 10 wt% to about 90 wt% of at least one tackifier.

16. The adhesive composition of claim 15, wherein said styrenic block copolymer is
15 selected from the group consisting of styrene-ethylene/butylene-styrene, styrene-isoprene-styrene, styrene-ethylene/butylene, styrene-ethylene/propylene, and mixtures thereof.

17. The adhesive composition according to one of claims 15 and 16, wherein said
20 styrenic block copolymer is a styrene-isoprene-styrene block copolymer having a styrene content of less than about 25 wt%.

18. The adhesive composition according to any one of claims 15-17, wherein said
25 ethylene/ α -olefin interpolymers are homogeneous linear or substantially linear interpolymers of ethylene and at least one C_3 to C_{20} α -olefin.

19. The adhesive composition according to any one of claims 15-18, wherein said ethylene/ α -olefin interpolymers have a density of less than about 0.885 g/cm^3 .

30 20. A double-faced tape formed from a radiation curable adhesive composition, said double-faced tape having a first surface and a second opposing surface, said first surface

exhibiting a first 180° peel value and said second surface exhibiting a second 180° peel value that is greater than said first peel value, upon radiation curing.

21. The double-faced tape according to claim 20, wherein the ratio of the second peel value to the first peel value is from about 2 to 1 to about 20 to 1.
22. The double-faced tape according to one of claims 20 and 21, wherein said adhesive composition comprises at least one block copolymer and at least one tackifier, said block copolymer having at least a first polyvinyl aromatic block and a second polydiene block having vinyl functionality; and wherein said block copolymer crosslinks through said vinyl functionality.
23. The double-faced tape according to any one of claims 20-22, wherein a source of said radiation curing is an Ultraviolet light.
24. A method of producing the double-faced tape according to any one of claims 20-23 comprising steps of:
- a) applying an adhesive composition onto a release coated surface to form an adhesive film having a first surface and a second opposing surface; and
 - b) curing said adhesive composition by means of radiation such that the first surface exhibits a first peel value and the second surface exhibits a second peel value that is greater than the first peel value.
25. The method according to claim 24, wherein the ratio of the second peel value to the first peel value is from about 2 to 1 to about 20 to 1.
26. The method according to one of claims 24 and 25, wherein said curing is carried out by using an Ultraviolet light.

27. A plastic wrap comprising a film and an adhesive composition according to any one of claims 1-9 disposed on one surface of said film, wherein said adhesive composition has a storage modulus of less than 1×10^5 dynes/cm² at 25°C.

5 28. A hook substrate bonded to a second substrate with an adhesive composition according to any one of claims 10-14.

29. A loop substrate bonded to a second substrate with an adhesive composition according to any one of claims 10-14.

10

30. A medical device having an adhesive composition according to any one of claims 1-9 that is intended to contact skin.

15 31. A medical device having an adhesive composition according to any one of claims 10-14 that is intended to contact skin.

32. A disposable article having at least one substrate bonded with an adhesive composition according to any one of claims 1-9, wherein said adhesive composition is in contact with an oil-based ingredient.

20

33. A disposable article having at least one substrate bonded with an adhesive composition according to claim 8, wherein said adhesive composition is in contact with an oil-based ingredient.

25 34. A radiation curable adhesive composition comprising:
a) from about 10 wt-% to about 50 wt-% of at least one block copolymer having at least two blocks wherein the first block is a polyvinyl aromatic block and the second block is a polydiene block having vinyl functionality;
b) from about 20 wt% to about 55 wt-% of at least one tackifier;
30 c) from about 10 wt% to about 40 wt-% of at least one wax; and
d) from about 0 wt% to about 35 wt% of at least one plasticizer.

35. The adhesive composition of claim 34, wherein said adhesive composition is substantially nontacky at a temperature lower than the cloud point of said wax.

5 36. The adhesive composition according to one of claims 34 and 35, wherein said adhesive composition is cured at a temperature above the cloud point of said wax.

37. A filmic label having the adhesive composition according to any one of claims 34-36, said adhesive has excellent performance under stress and heat, which allows said
10 label to shrink upon exposure to heat such that the seam remains sealed tightly.

15

20

25

30




FIG.1




FIG.2

3/4


TEMP [$^{\circ}\text{C}$]

FIG. 3

4/4




FIG.4

INTERNATIONAL SEARCH REPORT

Interr. Application No

PCT/US 01/02807

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09J153/02 C09J7/02 A61L15/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 719 226 A (KEGLEY LARRY MCARTHUR) 17 February 1998 (1998-02-17) examples ---	1-9
X	US 5 932 648 A (KEGLEY LARRY MCARTHUR ET AL) 3 August 1999 (1999-08-03) examples claims ---	1-9
X	US 5 614 577 A (SASAKI YUKIHIKO ET AL) 25 March 1997 (1997-03-25) examples ---	10-17
X,P	WO 00 22062 A (SHELL INT RESEARCH) 20 April 2000 (2000-04-20) the whole document --- -/--	1-19, 34-36

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *8* document member of the same patent family

Date of the actual completion of the international search

23 May 2001

Date of mailing of the international search report

07/06/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pollio, M

INTERNATIONAL SEARCH REPORT

Interr. ial Application No

PCT/US 01/02807

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 093 406 A (LOSSNER KEVIN S ET AL) 3 March 1992 (1992-03-03) claim 1	1-19, 34-36
A	--- US 5 773 506 A (MA JINGJING ET AL) 30 June 1998 (1998-06-30) column 6, line 52 - line 61	1-37
A	--- US 5 891 957 A (KORPMAN RALF ET AL) 6 April 1999 (1999-04-06) the whole document -----	1-37

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Patent Application No

PCT/US 01/02807

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5719226 A	17-02-1998	AU 702857 B	04-03-1999
		AU 7129696 A	01-04-1997
		BR 9610498 A	30-03-1999
		CN 1198768 A	11-11-1998
		DE 69602611 D	01-07-1999
		DE 69602611 T	21-10-1999
		DK 850284 T	08-11-1999
		WO 9710310 A	20-03-1997
		EP 0850284 A	01-07-1998
		ES 2131961 T	01-08-1999
		JP 11512468 T	26-10-1999
		TR 9800473 T	22-06-1998
		ZA 9607696 A	17-03-1997
US 5932648 A	03-08-1999	NONE	
US 5614577 A	25-03-1997	US 5302649 A	12-04-1994
		US 4948825 A	14-08-1990
		AT 170539 T	15-09-1998
		AU 1947388 A	04-01-1989
		AU 622619 B	16-04-1992
		BR 8807085 A	17-10-1989
		CA 1333829 A	03-01-1995
		DE 3856246 D	08-10-1998
		DE 3856246 T	21-01-1999
		EP 0316435 A	24-05-1989
		ES 2006968 A	16-05-1989
		JP 2500198 T	25-01-1990
		KR 9703953 B	24-03-1997
		WO 8809800 A	15-12-1988
		US 5093406 A	03-03-1992
		US 5135978 A	04-08-1992
		US 5115008 A	19-05-1992
WO 0022062 A	20-04-2000	AU 6472099 A	01-05-2000
US 5093406 A	03-03-1992	US 4948825 A	14-08-1990
		AT 170539 T	15-09-1998
		AU 1947388 A	04-01-1989
		AU 622619 B	16-04-1992
		BR 8807085 A	17-10-1989
		CA 1333829 A	03-01-1995
		DE 3856246 D	08-10-1998
		DE 3856246 T	21-01-1999
		EP 0316435 A	24-05-1989
		ES 2006968 A	16-05-1989
		JP 2500198 T	25-01-1990
		KR 9703953 B	24-03-1997
		WO 8809800 A	15-12-1988
		US 5614577 A	25-03-1997
		US 5302649 A	12-04-1994
		US 5135978 A	04-08-1992
		US 5115008 A	19-05-1992
US 5773506 A	30-06-1998	AU 706100 B	10-06-1999
		AU 4700396 A	23-09-1996
		BR 9607692 A	07-07-1998
		CA 2213298 A	12-09-1996

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No

PCT/US 01/02807

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5773506 A		CN 1177369 A	25-03-1998
		DE 69604278 D	21-10-1999
		DE 69604278 T	27-04-2000
		EP 0813581 A	29-12-1997
		JP 11501076 T	26-01-1999
		WO 9627644 A	12-09-1996
US 5891957 A	06-04-1999	BR 9705118 A	15-09-1998
		CN 1183447 A	03-06-1998
		EP 0838510 A	29-04-1998
		JP 10152663 A	09-06-1998
		TR 9701249 A	21-05-1998